

Physical Properties	Unit	Value
Intrinsic Viscosity	dl/g	0.80
Acetaldehyde	ppm	1.00
Heat deflection temp (Unannealed)	deg C	87
Heat deflection temp (Annealed)	deg C	100
Water Absorbtion (24hr, 23c)	%	0.15
Glass transition temp	deg C	82
Light transmittance	%	95

Mechanical Properties	Unit	Value
Tensile modulus	MPa	2500
Tensile strength	MPa	64
Yield stress	MPa	61
Flexural modulus @ 23c	MPa	2200
Izod notched impact strength @23c	kJ/m^2	7.5